

Claims

1. (Currently Amended) A process for producing a bio-catalyst, comprising the following steps:

- a) ~~utilizing an aqueous polyvinyl alcohol solution with a degree of hydrolysis of at least 98 mol%;~~
- a) utilizing an aqueous polyvinyl alcohol solution wherein the polyvinyl alcohol has a degree of hydrolysis of at least 98 mol%;
- b) dissolving an additive in the aqueous polyvinyl alcohol solution which, if the overall solution is concentrated, forms a finely distributed aqueous phase separated from the polyvinyl alcohol solution;
- c) adding a biologically active material selected from the group consisting of microorganisms, enzymes, spores, and cells;
- d) dehydrating the overall solution up to a maximum residual water content of 50 wt.% in order to cause the phases to separate and the polyvinyl alcohol to gel; and
- e) rehydrating the polyvinyl alcohol, including the biologically active material, in an aqueous medium.

2. (Currently Amended) The process according to Claim 1, wherein the polyvinyl alcohol solution has a concentration of 4 - 30 wt.%, exclusive of the additive and exclusive of the biologically active material.

3. (Currently Amended) The process according to Claim 1, wherein the polyvinyl alcohol solution has a concentration of 6 - 16 wt.%, exclusive of the additive and exclusive of the biologically active material.

4. (Previously Amended) The process according to Claim 1, wherein the additive is used which has an affinity to water at least similar to that of the polyvinyl alcohol.

5. (Previously Amended) The process according to Claim 4, wherein the additive is selected from the group consisting of cellulose esters, cellulose ethers, starch esters, starch

ethers, polyalkylene glycol ethers, polyalkylene glycols, long-chain alkanols ($n \geq 8$), sugar esters and sugar ethers.

6. (Original) The process according to Claim 1, wherein the additive includes polyethylene glycol.

7. (Currently Amended) The process according to Claim 6, wherein the additive has a concentration in a range of 4 - 20 wt.% , exclusive of the additive and exclusive of the biologically active material.

8. (Currently Amended) The process according to Claim 6, wherein the additive has a concentration in a range of 6 - 10 wt.% , exclusive of the additive and exclusive of the biologically active material.

9. (Original) The process according to Claim 1, wherein the dehydration of the aqueous solution is performed until a residual water content of at least 10 wt.% is reached.

10. (Original) The process according to Claim 1, wherein the dehydration of the aqueous solution is performed until a residual water content in a range of 10 - 30 wt.% is reached.

11. (Original) The process according to Claim 1, wherein the dehydrating of the aqueous solution is performed after dripping the aqueous solution onto a hard surface.

12. (Original) The process according to Claim 1, wherein the dehydrating of the aqueous solution is performed after pouring the aqueous solution into a form.

13. (Currently Amended) The process according to Claim 1, wherein ~~the a~~ gel substance ~~is formed with~~ form has a diameter that is at least double a height of the gel substance.

14. (Currently Amended) The process according to Claim 1, wherein ~~the a~~ gel substance ~~is formed with~~ form has a diameter of at least 1 mm and a height in a range between 0.1 and 1 mm.
15. (Currently Amended) The process according to Claim 1, wherein ~~the a~~ gel substance ~~is formed with~~ form has a diameter in a range of between 2 mm and 4 mm and a height in a range between 0.2 mm and 0.4 mm.
16. (Original) The process according to Claim 1, wherein the dehydrating of the aqueous solution is performed after pouring the aqueous solution to form a long strand.
17. (Original) The process according to Claim 1, wherein the dehydrating of the aqueous solution is performed after pouring the aqueous solution onto a base material.
18. (Original) The process according to Claim 1, wherein the rehydrating the polyvinyl alcohol is performed in water.
19. (Original) The process according to Claim 1, wherein the rehydrating the polyvinyl alcohol is performed in a saline solution.
20. (Cancelled)
21. (Original) The process according to Claim 20, wherein a culture solution for the biologically active material is used as the saline solution.
22. (Original) The process according to Claim 21, wherein said culture solution contains polyvalent anions.
23. (Original) The process according to Claim 1, wherein additives, which alter specific gravity are added to the solution prior to dehydration.

24. (Currently Amended) The process according to Claim 1, wherein the dehydrating of the aqueous solution is completely performed during a falling process in a drop tower and occurs during the time it takes a created a drop to fall in the drop tower.

25. Withdrawn

26. Withdrawn


27. Withdrawn

28. Withdrawn

29. Withdrawn

30. Withdrawn

Respectfully submitted,



Robert C. Haldiman, Reg. No. 45,437
Husch & Eppenberger, LLC
401 Main Street, Suite 1400
Peoria, Illinois 61602-1241
(309) 637-4900